#### Heavy Duty Coating | Page 1 TOA **Supershield Aqua Gloss** Topcoat

## **Technical Data Sheet**



Rev. 1 10/2017

#### **FEATURES**

Acrylic Waterborne is a new technology, ambient cured, one component acrylic coating with superior exterior performance properties. Provides outstanding abrasion resistance, good chemical resistance, excellent color and gloss retention.

This product is designed as a finish gloss waterborne coating for facilities applications such as hospitals, school, nursing homes, commercial building or industrial plants

- : Hardness film Acrylic waterborne for steel, galvanize, wall and wood.
- : Abrasion resistance.
- : Low VOC
- : Chemical and stain resistance.
- : Easy application, Odorless and fast dry.
- : Easy washed and cleaned.
- : No contained Lead and Mercury.
- : Safety health for user and tenant.
- : Suitable for general factory, food industry, phamaceutical industry, dairies food center, canteen, school, nursing home, hospital, hotel, department store and supermarket.

#### TECHNICAL INFORMATION

Type : Acrylic Emulsion Paint : Wide range of colors Color

: Gloss Film appearance

 $1.24 \pm 0.02$ Specific gravity : 36 ± 2 % Solid by volume  $:51 \pm 2\%$ Flash point

: N/A Wet film thickness

: 100 - 110 microns Dry film thickness : 35 - 40 microns Practical coverage. : 35 - 45 m<sup>2</sup>/ gal

> Remark: Actual Surface coverage will depend on surface irregularities, Mixing, Application Condition method and technique; as well as the structure and dimensions of the object to be coated.

> > 35 °C

30°C

Temperature Touch dry Surface dry 10 mins 9 mins 8 mins Full cure 1.5 hrs. 45 mins Hard dry 1 hrs. Recoat dry Minimum 1.5 hrs. 45 mins 1 hrs.

25 °C

#### **FILM PERFORMANCE**

- : Suitable for use on structural surface on surface where there is a possibility of incidental, food contact in commercial food preparation establishments, food processing plant and federally inspected meat and poultry plants.
- : QUV 1,200 Hours Test : Yellowness
- : Odorless & No flash point problems.

#### REFERENCE STANDARD

: TIS.2321-2549 (Weather Resistant Emulsion Paints) Green Label Thailand

Heavy Duty Coating Page 2 TOA **Supershield Aqua Gloss Topcoat** 

## **Technical Data Sheet**



Rev. 1 10/2017

#### **APPLICATION**

Tools : Air spray, Brush, Roller : Maximum 85% RH Humidity

Thinner · Water

Dilution (%) : 10- 15% by volume for Roller or Brush

: 10-20% by volume for Spray

#### **APPLICATION SYSTEM**

#### Surface Preparation

**New Surface Concrete** Old Surface Concrete

- Structure Coating Surface
- Wood Coating Surface

- : Substrate must be completely cured and dried (~1 month) free from oil, grease, mildew.
- : Powdery and chalky surface must be scrubbed and cleaned with water. Fungus and mildew growth must be cleaned off. Left to dry for 2-3 days. For more smooth surface use TOA Acrylic Wall Filler for skim coating.
- : The surface must be clean, dry, free of loose rust and scale paint, etc. Remove all oil, grease and other contaminants with a suitable solvent. Metal should be blast cleaned in accordance with NACE No.2 / SSPC-SP10, ISO 8501:1, SIS Sa 2.5 to a near-white finish using a suitable abrasive or Power tool cleaning in accordance with SIS St 3 or SSPC-SP3.
  - : Surface repair (cracks, pores, holes) done with TOA Epoxy putty and polishing of surface with moltoprene disk.
- : Use TOA abrasive paper no. 240-320 to sand the wood surface until smooth, Fill all wood crack and hole by filler Sand again until the smooth surface is obtain, Clean the surface until no dust remain

#### Coating System

**Protective Coating** : Primer Supershield Aqua Gloss Primer 40 microns x 1 coat

Supershield Aqua Gloss : Topcoat 40 microns x 2 coats

Recommendation : The proper relative humidity in the work shall not exceed 85% RH.

> : The temperature of the substrate should be minimum 10°C and at least 3°C above the dew point of the air, temperature and relative humidity measured in the vicinity of the substrate for prevent moisture and water drop on substrate effective adhesion and drying time.

#### HANDLING AND STORAGE

: The product must be stored in accordance with national regulations. Storage conditions are to keep Storage condition

the containers in a dry, cool, well ventilated space and away from source of heat and ignition.

Shelf life : 24 months at 30-35 °C

1 Gallon, 1/4 Gallon Package

TOA
Supershield Aqua Gloss
Topcoat

## **Technical Data Sheet**



Rev. 1 10/2017

#### **HEALTH AND SAFETY**

- : Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.
- : For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Safety Data Sheet.

#### **DISCLAIMER**

: The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything only the quality of the product itself. We reserve the right to change the given data without notice.

ทีโอเอ

สีอุตสาหกรรมหนัก หน้า : 1

ซุปเปอร์ชิลด์ อะควา กลอส ท็อปโค๊ต

## ข้อมูลทางวิชาการ



ทบทวนครั้งที่ 1 10/2560

0010	III IM
คณสเ	ולונונו

เป็นสีเคลือบประเภทอะครีลิคโมดิฟายด์การแห้งฟิล์มด้วยตัวเอง สูตรน้ำ มีกลิ่นอ่อนและระเหยตัวได้รวดเร็ว มีคุณสมบัติเด่น ให้ฟิล์มสีมีความเงา ทนทานต่อการถูกทำลายโดยรังสีเหนือม่วงจากแสงแดด ปราศจากสารปรอทและตะกั่วแล้วยังประกอบด้วยผงสีคุณภาพสูง ที่มีความเหมาะสมกับสภาพอากาศเมืองร้อน และเพิ่มสารการยึดเกาะ ให้การยึดเกาะดีเยี่ยมบนพื้นผิวเกือบทุกชนิด สามารถใช้กับพื้นผิวผนังคอนกรีต, โครงสร้างที่เป็นเหล็ก, กัลวาไนซ์ และไม้ ที่ผ่านการรองพื้นอย่างเหมาะสมทั้งภายในและภายนอกอาคารและใช้งานได้ดีใน โรงเรียน โรงพยาบาล โรงแรม โรงงานอุตสาหกรรมประเภทยา / อาหาร ซึ่งมีกลิ่นอ่อนและแห้งไว

#### ข้อมูลทางเทคนิค

**ประเภทของสี** อะครีลิค

เฉคสี สามารถเลือกได้จากเฉคสีในแคตตาลอคและเครื่องผสมสีอัตโนมัติ

ไม่มี

ลักษณะฟิล์มสี

ความถ่วงจำเพาะ  $1.24 \pm 0.05$  เนื้อสีโดยปริมาตร  $36 \pm 2 \%$  เนื้อสีโดยน้ำหนัก  $51 \pm 2 \%$ 

จุดวาบไฟ

**ความหนาฟิล์มสีเมื่อเปียก** 100 - 110 ไมครอน **ความหนาฟิล์มสีเมื่อแห้ง** 35 - 40 ไมครอน

**การครอบคลุมพื้นที่ (ปฏิบัติ)** 35-45 ตารางเมตร / แกลลอน / เที่ยว

หมายเหตุ : การผสม, การใช้งาน, ความหยาบและรูพรุนของพื้นผิว มีผลต่อการปกคลุมพื้นผิว

25 °c 30 °c 35 °c อุณหภูมิ ระยะเวลาแห้งสัมผัส แห้งผิว 10 นาที 9 นาที 8 นาที แห้งแง็ง 1.5 ชั่วโมง 1.0 ชั่วโมง ระยะเวลาแห้งสมบูรณ์ 45 นาที 1.5 ชั่วโมง 1.0 ชั่วโมง ระยะเวลาแห้งทาทับ 45 นาที

> หมายเหตุ : การระบายอากาศ อุณหภูมิ ความหนาของฟิล์มสี และจำนวนชั้นของฟิล์มสี จะมีผลกระทบ และสัมพันธ์กับระยะเวลาในการแห้งของฟิล์มสี

### มาตรฐานอ้างอิง

**ใบรับรองจากสถาบันภายนอก** มอก.2321-2549 (มาตรฐานอุตสาหกรรม สีอิมัลซัน เกรดทนสภาวะอากาศ)

ฉลากเขียวไทย

#### วิธีใช้งาน

อุปกรณ์ เครื่องพ่น, แปรง, ลูกกลิ้ง

**ทินเนอร์** น้ำสะอาด

**การผสมทินเนอร์ (%)** ผสมน้ำ 10-15 % โดยปริมาตร เมื่อใช้ลูกกลิ้ง หรือแปรง

ผสมน้ำ 10-20 % โดยปริมาตร เมื่อใช้เครื่องพ่น

ทีโอเอ

สีอุตสาหกรรมหนัก | หน้า : 2

ซุปเปอร์ชิลด์ อะควา กลอส ท็อปโค๊ต

# **ข**้อมูลทางวิชาการ



ทบทวนครั้งที่ 1 10/2560

	ทบทวนครั้งที่ 1 10/2560	
ระบบการใช้งาน การเตรียมพื้นผิว	พื้นผิวปูนใหม่ : ทิ้งผนังให้แห้งอย่างน้อย 1 เดือน ทำความสะอาดผนังให้ปราศจากเศษฝุ่นผง เศษซีเมนต์ และคราบโง  พื้นผิวปูนเก่า : งัดล้างสีเดิมที่เสื่อมสภาพออกให้หมด ล้างทำความสะอาด แล้วทิ้งให้แห้ง 1-2 วัน บริเวณที่มีรอยแตกร้าวความกว้างน้อยกว่า 1 มม. และไม่แตกต่อเนื่อง ให้อุดโป๊วด้วยทีโอเอ อะครีลิค ฟิลเลอร์ บริเวณที่มีรอยแตกร้าว ความกว้างมากกว่า 1 มม. หรือมีการแตกต่อเนื่อง ให้อุดโป๊วด้วย ทีโอเอ อะครีลิค ซิลแลนท์  พื้นผิวโครงสร้างเหล็ก : ต้องแห้งสนิทปราศจากคราบไงมัน และสิ่งสกปรก ทำความสะอาดให้ได้ระดับอย่างน้อย NACE No.2 หรือ SSPC-SP10, ISO 8501:1, SIS Sa 2.5 หลังพ่นทรายควรเอาฝุ่นออกให้หมด แล้วค่อยเคลือบสี บริเวณที่มีรอยแตกร้าวความกว้างน้อยกว่า 1 มม. และไม่แตกต่อเนื่อง ให้อุดโป๊วด้วยทีโอเอ อีพือกซี่ พุตตี้  พื้นผิวไม้ : งัดกระดาษทราย เบอร์ 240-320 ให้เรียบเนียน บริเวณที่มีรอยแตกร้าว ให้อุดโป๊วด้วยฟิลเลอร์ให้เรียบร้อย	
ระบบการทาสี	และทำการขัดกระดาษ พร้อมขจัดฝุ่นให้พื้นผิวสะอาด : สีรองพื้น ซุปเปอร์ชิล อะควา กลอส ไพร์เมอร์ ไวท์ จำนวน 1 เที่ยว : <b>สีทับหน้า ซุปเปอร์ชิลค์ อะควา กลอส ท็อปโค๊ต จำนวน 2 เที่ยว</b>	
การเก็บรักษา สภาวะการเก็บรักษา อายุผลิตภัณฑ์ ขนาดบรรจุ	: สินค้าจำเป็นต้องเก็บรักษาตามข้อกำหนด ควรเก็บในที่แห้ง มีอากาศถ่ายเทดี ไม่ควรเก็บในที่ร้อน และไม่ให้ถูกแสงแดดโดยตรง : 24 เดือน ที่อุณหภูมิ 30-35 °C : 1 แกลลอน, 1/4 แกลลอน	
<ul><li>ข้อมูลสุขภาพและความปลอดภัย</li></ul>	: กรุณาดูข้อควรระวังที่ติดไว้หน้ากระป๋อง การทำงานสีควรทำในที่ที่อากาศถ่ายเทได้สะดวก อย่าสูดหายใจ เอาละอองสีเข้าไปโดยตรง ควรใส่หน้ากากเมื่อทำการพ่นสี และพยายามเลี่ยงมิให้สัมผัสผิวหนังโดยตรง ถ้าสีสัมผัสผิวหนังควรล้างด้วยน้ำสะอาด และสบู่ทันที หากกระเด็นเข้าตาควรล้างด้วยน้ำสะอาดทันที แล้วรีบไปพบแพทย์ : รายละเอียดด้านความปลอดภัยเกี่ยวกับการใช้ผลิตภัณฑ์ ระบุไว้ในเอกสารข้อมูลความปลอดภัย (SDS)	
การสงวนสิทธิ์เรียกร้อง	: รายละเอียดข้างบนนี้ได้มาจากการทดลอง และจากประสบการณ์ที่ผ่านมา เนื่องจากผลิตภัณฑ์ถูก นำไปใช้ในภาวะที่แตกต่างกัน จึงไม่สามารถรับประกันในสิ่งใดนอกเหนือจากคุณภาพของ ผลิตภัณฑ์เท่านั้น บริษัทขอสงวนสิทธิ์ในการเปลี่ยนแปลงข้อมูลโดยไม่ต้องแจ้งล่วงหน้า	