

Technical Data Sheet



Rev. 1 10/2017

FEATURES

: Floorguard Primer is a two pack epoxy and polyamide clear for concrete primer
 As a primer for concrete surface on epoxy system in factory floor. It has an excellent properties for adhesion and penetrate into concrete surface, abrasion resistance, resistance to water, weak acid, weak basic and chemical

TECHNICAL INFORMATION

Type	: Epoxy / Polyamide Primer		
Color	: Clear		
Film appearance	: Gloss		
Specific gravity	: 1.03 ± 0.05		
Solid by volume	: $55 \pm 2\%$		
Flash point	: 28°C		
	Minimum	Maximum	Recommended
Dry film thickness	(Microns)	40	60
Wet film thickness	(Microns)	73	109
Theoretical coverage	$\text{m}^2 / \text{Liter}$	13.8	9.2
	$\text{m}^2 / \text{Gallon}$	52.0	34.7
Practical coverage	$\text{m}^2 / \text{Liter}$	9.6	6.4
	$\text{m}^2 / \text{Gallon}$	36.0	24.0
Remark : Actual Surface coverage will depend on surface irregularities, Mixing, Application Condition method and technique; as well as the structure and dimensions of the object to be coated.			
Touch dry	Temperature	25°C	30°C
	Surface dry	4 hrs.	3 hrs.
Full cure	Hard dry	14 hrs.	13 hrs.
	Minimum	16 hrs.	12 hrs.
Recoat dry	Maximum	2 days	2 days
		10 hrs.	9 hrs.
Remark : Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly.			

APPLICATION

Mixing Ratio	Part A	Part B
By Volume	4	1
By Weight	5	1
Application Method	Airless Spray	Air Spray
Diluted by	-	15-20
TOA Thinner 31		10-15
Applicator	-	Conventional Spray (Iwata) Short Hair Stiff Nylon Roller (Stanley) Stiff Nylon Brush
Pressure	-	3-4 kg/cm ²

Mix Part A and Part B, strictly follow mix ratio recommendations before dilute by Thinner mixing and stir for 2-3 minutes until the mixture is homogeneous after leave 5 minutes before application.

**APPLICATION SYSTEM****Surface Preparation**Floor

- : For New concrete - The concrete prior to laying plastic sheets to block moisture from underground. Then it should be left for curing concrete to solid and dry for about 3-4 weeks. Then, clean the surface free from dust, dirt, grease and most importantly, the surface is completely dry. (Check moisture content must be less than 10%)
- : For Old concrete - To remove the old paint film which loosely adhesion to as much as possible by Scraping with a shovel or Grinding machine to enhance adhesion. Then, clean the surface free from grease and oil with suitable solvent. Before primer coating should clean all surfaces free from dust, dirt, grease and most importantly, the surface is completely dry. (Check moisture content must be less than 10%).
- : For Floor Hardener or Surface glossy finish :
- : Concrete surface preparation by using dust free captive blasting units, grinding equipment, sand blasting for increase adhesion of coating.
- : Inspect the concrete for bug holes void, fin and other imperfections. Protrusions shall be ground smooth while voids shall be filled with Floorguard Putty or other suitable filler and polishing of surface with moltoprene disk.
- : After cleaning, repair surface defects and remove deteriorated previous coatings.
- (Check moisture content must be less than 10%).

Before Recoat by Topcoat

- : Remover all oil, grease, dirt, oxide and other foreign material by cleaning per SSPC-SP1, Solvent Cleaning before coating.
- : If over 7 days gives cleaning surface by sand paper no. 320-400 and cleaning surface per SSPC-SP1, Solvent Cleaning before coating.
- : Surface repaire (cracks, pores, holes) done with Floorguard Putty and polishing of surface with moltoprene disk.

Coating SystemFor Interior**Concrete protective Coating**

: Primer	Floorguard Primer	50 microns x 1 coat
: Topcoat	Floorguard 100 (for inside area)	50 microns x 2 coats
	or	
: Topcoat	Floorguard PU 100 (for outside area)	50 microns x 2 coats

Recommendation

- : The proper relative humidity in the work shall not exceed 85% RH.
- : The temperature of the substrate should be minimum 10°C and at least 3°C above the dew point of the air, temperature and relative humidity measured in the vicinity of the substrate for prevent moisture and water drop on substrate effective adhesion and drying time.

HANDLING AND STORAGE**Storage condition**

: The product must be stored in accordance with national regulations. Storage conditions are to keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition.

Shelf life

: 24 months at 30-35 °C

Package

Packaging size	Part A :	Part B :
1 Gallon Set	1 Gallon	1/4 Gallon

Technical Data Sheet



Rev. 1 10/2017

HEALTH AND SAFETY

- : Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.
- : For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Safety Data Sheet.

DISCLAIMER

- : The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything only the quality of the product itself. We reserve the right to change the given data without notice.

คุณสมบัติ

: ฟลอร์การ์ด ไพรเมอร์ เป็นสีรองพื้นอีพ็อกซี่ 2 ส่วน สำหรับผิวคอนกรีต ประกอบด้วยอีพ็อกซี่เชื่อม
และโพลีอีปโตรเซน มีคุณสมบัติเด่นพิเศษ ในการแทรกซึมแท้ไปในพื้นผิวคอนกรีตได้ดีเยี่ยม
มีคุณสมบัติในการยึดเกาะ, ความทนทาน, ความแข็ง และความทนเนื้าที่ดีเยี่ยม
เหมาะสมสำหรับใช้ทาเป็นสีรองพื้นเบนซินพิวคอนกรีต ในระบบอีพ็อกซี่ มีคุณสมบัติในการยึดเกาะ
และแทรกซึมลงสู่พื้นผิวได้ดี ตลอดจนทนทานต่อน้ำ, กรดอ่อน, ด่างอ่อน, สารเคมี, การขัดถู

ข้อมูลทางเทคนิค

ประเภทของสี	: สีรองพื้นอีพ็อกซี่
สีดีไซน์	: ใส
ลักษณะพิเศษ	: เจาะ
ความถ่วงจำเพาะ	: 1.03 ± 0.05
เนื้อสีโดยปริมาตร	: $55 \pm 2\%$
จุดควบไฟ	: 28 องศาเซลเซียส

	ไม่น้อยกว่า	ไม่มากกว่า	แนะนำ
ความหนาพิเศษเมื่อแห้ง	(ไมครอน)	40	60
ความหนาพิเศษเมื่อเปียก	(ไมครอน)	73	109
การครอบคลุมพื้นที่ (กغمร.)	(ตร.ม. / สิตร.)	13.8	9.2
	(ตร.ม. / แกลลลอน)	52.0	34.7
การครอบคลุมพื้นที่ (ปฏิบัติ)	(ตร.ม. / สิตร.)	9.6	6.4
	(ตร.ม. / แกลลลอน)	36.0	24.0

หมายเหตุ : การผสม, การใช้งาน, ความหมายและรูปแบบของพื้นผิว มีผลต่อการปิดคลุมพื้นผิว

อุณหภูมิ	25 °C	30 °C	35 °C
แห้งผิว	4 ชั่วโมง	3 ชั่วโมง	2 ชั่วโมง
แห้งแข็ง	14 ชั่วโมง	13 ชั่วโมง	12 ชั่วโมง
อย่างน้อย	16 ชั่วโมง	14 ชั่วโมง	12 ชั่วโมง
อย่างมาก	2 วัน	2 วัน	2 วัน
	10 ชั่วโมง	9 ชั่วโมง	8 ชั่วโมง

หมายเหตุ : การระบายอากาศ อุณหภูมิ ความหนาของพิเศษ และจำนวนชั้นของพิเศษ จะมีผลต่อ
และสับพันธ์กับระยะเวลาในการแห้งของพิเศษ

วิธีใช้งาน

อัตราส่วนผสม	ส่วน เอ	ส่วน บี
โดยปริมาตร	4	1
โดยน้ำหนัก	5	1
วิธีการใช้งาน	Airless Spray	Air Spray
เจือจางด้วย	-	15-20
กีโอเอ กิบเนอร์ เบอร์ 31	-	10-15
เครื่องมือที่ใช้	-	ปืนพ่นสี (Iwata) ลูกกลั้งขนสั้น (Stanley) ประปาสี
แรงดัน	-	3-4 กก./ตร.ซม.

แนะนำให้ผสมสีส่วน เอ และส่วน บี ตามอัตราส่วนที่กำหนดให้เข้ากันก่อนเจือจางด้วยกิบเนอร์ในปริมาณที่แนะนำ
จากนั้นกวนส่วนผสมต่อไปอีก 2-3 นาที จนเป็นเนื้อเดียวทั่วทั้ง แล้วตั้งทิ้งไว้ 5 นาที ก่อนนำไปใช้งาน

ระบบการใช้งาน

การเตรียมพื้นผิว

พื้นคอนกรีตคอนกรีตขัดมัน (Floor Hardener)

ก่อนเคลือบสีชั้นต่อไป

- : ให้ทำการขูดและเชปูน หรือสีง่ายปломบ์ต่างๆออกให้หมด กรณีที่พื้นผิวมีฟลัมสีเดิมที่เสื่อมสภาพ เสียหายยึดเกาะ ให้ขูดเชปูนให้มากที่สุด แล้วจึงทำความสะอาดพื้นผิวให้ปราศจากคราบไขมัน สีสกปรก และฝุ่นผงต่างๆ ก่อนการทาสีพื้นผิวต้องแห้งสนิท (เช็คความชื้นได้ < 10%)
- : ขัดเปิดพื้นผิวให้หยาบ โดยใช้เครื่อง Grinding หรือเครื่อง Shot Blast เพื่อเสริมการยึดเกาะ :
- กรณีพื้นผิวที่มีรอยแตกร้าว เป็นร่องหลุม ทรุดไม่สม่ำเสมอ ให้ทำการอุดเป็น ช่องแซม ด้วยวัสดุอุดปูิว Floorguard Putty หลังขับตอนการทาสีรองพื้นเสร็จเรียบร้อยแล้ว หลังจากนั้นขัดตกแต่งพื้นผิวให้เรียบร้อยก่อนการทาสีกับหน้า (เช็คความชื้นได้ < 10%)
- : ทำการเช็ดทำความสะอาดพื้นผิวฟลัมสีด้วยตัวเอง ทำลายที่เหมะสมเพื่อกำจัดคราบฝุ่น, คราบไข, น้ำมัน, สารบี, ยางมะตอย, คราบเกลือ, สีสกปรก และสีส่วนเปื้อนต่างๆ ก่อนทาสี บนฟลัมสีด้วยทุกครั้งก่อนเคลือบสีชั้นต่อไป ตาม SSPC-SP1
- : หากก้นฟลัมสีไว้เกิน 7 วัน ให้ทำการขัดพื้นผิวของฟลัมสี หลังจากนั้นเช็ด ทำความสะอาดสะอาดต่อตัวเอง ตัวเอง ทำลายที่เหมะสมตาม SSPC-SP1 ก่อนที่จะเคลือบสี
- : กรณีพื้นผิวที่เป็นร่องหลุม ทรุดไม่สม่ำเสมอ ให้ทำการอุดปูิว ช่องแซมด้วยวัสดุอุดปูิว Floorguard Putty หลังขับตอนการทาสีรองพื้นเสร็จเรียบร้อยแล้ว จากนั้นขัดตกแต่งให้เรียบร้อย การยึดเกาะจะดีกว่าชั้นของฟลัมสี หลังจากนั้นเช็ด ทำความสะอาดต่อตัวเอง ทำลายที่เหมะสม ตาม SSPC-SP1 ก่อนที่จะเคลือบสี

ระบบการทาสี

สำหรับงานภายใน

งานพื้น

สีรองพื้น	ฟลอร์การ์ด ไพรเมอร์	50 ไมครอน x 1 เที่ยว
สีกับหน้า	ฟลอร์การ์ด 100	50 ไมครอน x 2 เที่ยว
	(สำหรับงานภายใน)	

หรือ

สีกับหน้า	ฟลอร์การ์ด พี.ยู 100	50 ไมครอน x 2 เที่ยว
	(สำหรับงานภายนอก)	

ข้อแนะนำในการปฏิบัติงาน

- : ความชื้นสัมพัทธ์ในบรรยากาศที่เหมะสมต้องไม่เกิน 85% RH
- : อุณหภูมิของพื้นผิวต้องสูงกว่า 10 °C และสูงกว่าจุดน้ำค้างอย่างน้อย 3 °C เพื่อป้องกันการเกิดหยดน้ำบนพื้นผิว ซึ่งจะเป็นผลต่อการยึดเกาะ และการแห้งแข็งของฟลัมสีได้

การเก็บรักษา

สภาวะการเก็บรักษา

- : สินค้าจำเป็นต้องเก็บรักษาตามข้อกำหนด ควรเก็บในที่แห้ง มีอากาศถ่ายเทดี ไม่ควรเก็บในที่ร้อน แสงไม่ได้ถูกแสงแดดโดยตรง

อายุผลิตภัณฑ์

- : 24 เดือน ที่อุณหภูมิ 30-35 °C

- : สินค้าจำเป็นต้องเก็บรักษาตามข้อกำหนด ควรเก็บในที่แห้ง มีอากาศถ่ายเทดี ควรปิดฝาให้แน่นตลอดเวลา ไม่ควรเก็บในที่ร้อนแสงโดยตรง

ขนาดบรรจุ

ขนาดบรรจุภัณฑ์	ส่วน เอ :	ส่วน บี :
ชุด 1 แกลลอน	1 แกลลอน	1/4 แกลลอน

ข้อมูลสุขภาพและความปลอดภัย

- : กรณีดูดซื้อควรระวังก่อติดไว้หน้ากระป๋อง การทำงานสีควรทำในที่远离อากาศถ่ายเทได้สะดวก อย่าสูดหายใจ เอลาส-องฟลีซเข้าไปโดยตรง ควรใส่หน้ากากเมื่อทำการพ่นสี และพยายามเลี่ยงมือให้สัมผัสผิวหนังโดยตรง ถ้าสีสัมผัสผิวหนังล้างด้วยน้ำสะอาด และสบู่กับที่ หากกระเด็นเข้าตาควรล้างด้วยน้ำสะอาดกับที่ แล้วรีบไปพบแพทย์
- : รายละเอียดด้านความปลอดภัยเกี่ยวกับการใช้ผลิตภัณฑ์ ระบุไว้ในเอกสารข้อมูลความปลอดภัย (SDS)

ข้อมูลทางวิชาการ



แบบบันคับที่ 2 เริ่มใช้ 01/08/2559

การสงวนสิทธิ์เรียกร้อง

: รายละเอียดข้างบนนี้ได้มาโดยการกดลง และจากประสบการณ์ที่ผ่านมา เนื่องจากสีถูกนำไปใช้ในภาวะที่แตกต่างกัน เราจึงไม่สามารถรับประกันในสิ่งเดียวได้นอกจากคุณภาพของสีเท่านั้น
: บริษัทขอสงวนสิทธิ์ที่จะเปลี่ยนแปลงข้อมูลโดยมิได้ต้องแจ้งล่วงหน้า